



Draft Data Sheet

UDMAX™ GPP 40-65 AO TAPE (0.28 mm)

DESCRIPTION

UDMAX™ GPP 40-65 AO TAPE is a UD glass reinforced, polypropylene based, composite material, produced using FRT's proprietary HPFIT™ technology, delivering optimal fiber spreading and a resin-rich surface layer at high fiber contents. UDMAX™ GPP 40-65 AO TAPE has been developed for applications such as composite tanks, that are submitted for long periods of time to continuous high pressure. The tape has high resistance to degradation, due to its optimized antioxidant and light stabilization package, resulting in a continuous long life performance. UDMAX™ GPP 40-65 AO TAPE is available in black, please contact our customer service department for available tape length and width, as well as winding method.

TYPICAL PROPERTIES VALUES

(Revision: 20200708)

Name	Typical values	Unit	Test methods
PHYSICAL			
Matrix material	PP-H		
Polymer melting point	166	°C	
Glass content	40	Volume%	-
Glass content	65	Weight%	-
Thickness	0.280	mm	-
Density	1.57	kg/dm ³	ISO1183
Areal weight	439	g/m ²	-
MECHANICAL			
Tensile modulus 0°	29	GPa	ISO 527-5
Tensile strength 0°	970	MPa	ISO 527-5

PROCESSING

It is not necessary to dry UDMAX™ GPP 40-65 AO TAPE prior to use. The recommended processing temperature range is 190° to 240°C, but the exposure to high temperatures should be kept to a minimum, to prolong degradation resistance. It is advised to allow newly shaped parts, produced using UDMAX™ GPP 40-65 AO TAPE, to cool down to 65°C or below, before further handling.

DISCLAIMER

Information and recommendations contained in this document are given in good faith. However, seller makes no express or implied representation, warranty or guarantee (i) that any results described in this document will be obtained under end use conditions, or (ii) as to the effectiveness or safety of any design or application incorporating seller's materials, products, services or recommendations. Brands marked with ™ are registered trademarks of FRT Tapes